

Serge Ferrari

Batyline
Lounge

Long lasting & sophisticated
outdoor fabric



Applications:


Upholstery for indoor & outdoor chairs, sofas, cushions



- **Simple elegance:** subtle colors with sophisticated depth.
- **Safe & durable:** phthalate free, GreenGuard certified, high resistance to outdoor conditions, fire resistant.
- **Easy:** dries quickly, easy to clean.

Batyline performance with
simple elegance





Quartz

7720FR-50932




White

7720FR-5701




Shea

7720FR-50931*



Saffron

7720FR-50929*



Cheyenne

7720FR-50928*



Reed

7720FR-50930*



Sage

7720FR-5049*




Zinc

7720FR-5703*




Sea spray

7720FR-50934*



Purple

7720FR-5708*



Abyss

7720FR-50935*



Dark alu

7720FR-5706*

Waterproof version also available,
please ask us for more information.

* Check for availability

Batyline

Lounge

7720FR

7721FR WP

■ Technical properties

Standards

Weight	14.8 oz/sqyd (500 g/m ²)	15.5 oz/sqyd (525 g/m ²)	EN ISO 2286-2
Width	55.1 in (140 cm)		

■ Physical properties

Abrasion resistance*	600,000 double rubs - Heavy Duty	ASTM D4157 Wyzenbeek
Tensile strength (warp/weft)	150 / 150 daN/5cm	EN ISO 1421
Tear strength (warp/weft)	18/15 daN	DIN 53.363
Light stability	GS=4 at 700 hrs	ASTM G154: UVA340
Colorfastness to light	4/5 > 1000 hrs	ASTM 4329
Mold resistance	Method A, degree 0, excellent	ISO 846-A
Extreme working temperatures	-22°F / +158°F	

■ Flame retardancy

United States	Pass	CALTB 117
Marine test	Pass	IMO MSC.307 (88) (2010 FTP Code) Annex 1 part 8

■ Management systems

Quality	ISO 9001
Environment	ISO 14001

■ Certification, labels, warranty



5 year warranty

Phthalate free

Smart Yarn

■ Tools and services

- Fabrication guide & cleaning instructions available upon request
- Visualize & play with custom colors and weaves with Serge Ferrari's Penelope Software.

*Multiple factors affect coated fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be a reliable indicator of increased coated fabric lifespan.

Quoted technical characteristics are average values with a +/- 5% tolerance. Our products are subject to improvements resulting from technical developments and we reserve the right to modify their characteristics at any time. The purchaser of our products is responsible for checking the above data.